ULTRA-GUARD FLASHPRENE UN

7 FLUID APPLIED | Flexible Flashing Accessory

GENERAL DESCRIPTION

Ultra-Guard Flashprene UN is a thermoset flashing material made of uncured neoprene rubber.

BASIC USE

Ultra-Guard Flashprene UN is typically used as the heavy-duty reinforcing and exposed flashing membrane in conjunction with GMX's Ultra-Guard HA 551 rubberized waterproofing membrane. Ultra-Guard Flashprene UN's unique properties provide ease in forming around penetrations and corners as well as detailing expansion / control joints and drains.

SIZES

The Ultra-Guard Flashprene UN membrane is available in a standard thickness of 60 mils (0.060 inch), standard widths of 12, and 18 inches, and a length of 100.5 feet.

TECHNICAL DATA | PRODUCT SPECIFICATIONS Type: Ultra-Guard Flashprene UN

Thickness, Inches ASTM D751	.060 + 10%
Width, inches ASTM D751	12, 18 inches
Length, Feet ASTM D751	100 + .5 foot
Tensile Strength, minimum PSI ASTM D412 Die C	1800
Elongation, Ultimate, minimum % ASTM D412	300
Tear Resistance, minimum, lbf/inch ASTM D624 Die C	175
Brittleness Point Temperature ASTM D746	-40°F
Ozone Resistance 168 hours/ 100 PPHM/104º F. 40ºC./50% ext ASTM D1149	No Cracks @ 7X magnification
Resistance to Water Absorption, % increase in weight max after 7 days @ 75° F. ASTM D471	1%



May help to contribute to LEED [®] credits:		
EA Credit 1:	Optimize Energy Performance	
EQ Credit 3.1:	Construction IAQ Management Plan: During Construction	
EQ Credit 4.2:	Low Emitting Materials: Paints and Coatings	
MR Credit 5.1:	Regional Materials: 10% Extracted, Processed and Manufactured Regionally	
MR Credit 5.2:	Regional Materials: 20% Extracted, Processed and Manufactured Regionally	

SHIPPING INFORMATION

Proper Shipping Name:	Non-regulated material Water-based asphalt emulsion
Hazard Class:	Not Applicable
Identification:	Not Applicable
Packaging Group:	Not Applicable

NOTE: Applies to DOT-U.S./ MOT-CANADA/INT'L (ALL MODES).

CAUTION: Ultra-Guard Flashprene UN is a water-based material. KEEP FROM FREEZING DURING TRANSIT AND STORAGE.



Results may differ based upon statistical variations depending upon mixing methods and equipment, temperatures, application methods, test methods, actual site conditions and curing conditions. Installation conditions and methods can impact product performance. Consult your local GMX Sales Representative for Questions.

PRIOR TO EACH USE OF ANY GMX PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS & INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT WWW.GMXCO.COM OR BY CALLING GMX AT 866-228-7743. NOTHING CONTAINED IN ANY GMX MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH GMX PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH GMX PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH GMX PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.