## DRAINMAX® 380





## TWO-PART GEOTEXTILE COMPOSITE DRAINAGE

## DESCRIPTION

DrainMax® 380 prefabricated sheet drain is composed of a dimpled polymeric core with a heavy-duty nonwoven geotextile bonded to the dimple side. The geotextile allows water to pass through while retaining backfill materials. The solid core allows water collection from one side and provides a continuous flow path to designated drainage exits. DrainMax® 380 is recommended for single-sided subsurface horizontal drainage applications requiring very high strength, moderate flow capacity, and a high-survivability geotextile.

TECHNICAL DATA		
Physical Properties <sup>1</sup>	Test Method	Typical Values
GEOTEXTILE		
Material <sup>2</sup>		PP, NPNW
Water Flow Rate	ASTM D4491	100 gpm/ft <sup>2</sup>
		4,075 Lpm/m <sup>2</sup>
Grab Tensile Strength	ASTM D4632	100 lbs
		445 N
CBR Puncture	ASTM D6241	580 lbs
		2,580 N
Trapezoidal Tear	ASTM D4533	80 lbs
		356 N
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D4751	80 sieve
		0.180 mm
Grab Elongation	ASTM D4632	60%
UV Resistance	ASTM D4355	70%/500 Hrs
Permittivity	ASTM D4491	1.5 sec <sup>1</sup>
CORE		
Thickness	ASTM D5199	0.25 in
		6.35 mm
Compressive Strength	ASTM D6364 /	30,000 psf
	ASTM D1621	1,436 kPa
In-Plane Flow Rate 4	ASTM D4716	13 gpm/ft
		161 Lpm/m
Perforated?		No
Backing Film for Softer Mem	branes	No
COMPOSITE		
Recycled Content 5	CALCULATED	> 70%
Roll Size	MEASURED	4 x 50 ft

**MEASURED** 

49 lbs

- Unless otherwise noted, all physical and performance properties listed are Typical Values as defined in ASTM D4439.
- 2. PP=Polypropylene; NPNW=Needle-Punched Nonwoven; WM=Woven Monofilament: for use in planters.
- 3. AOS value listed is Maximum Average Roll Value.
- In-plane flow rate measured under 3,600 psf (172 kPa) compressive load at hydraulic gradient of 1.0.
- 5. Pre-consumer recycled content by weight.
- 6. Approximate packaged roll weight.

All technical information contained in this document is accurate as of revision date listed. Please contact your GMX Account Manager for the most current technical information available.





GMX, Inc. 3014 Chamber Dr. Monroe, NC 28110 Toll Free: 866-228-7743 www.gmxwaterproofing.com

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperatures, application methods, test methods, actual site conditions and curing conditions. Installation conditions and methods can impact product performance. Consult your local GMX Sales Representative for Questions.

PRIOR TO EACH USE OF ANY GMX PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS & INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT WWW.GMXCO.COM OR BY CALLING GMX AT 866-228-7743. NOTHING CONTAINED IN ANY GMX MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH GMX PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

Roll Weight <sup>6</sup>