

ULTRA-GUARD® EFS



Multi-purpose Sealant

PRODUCT DESCRIPTION

Ultra-Guard® EFS is a high-performance joint sealant for a wide range of construction applications. Ultra-Guard® EFS delivers tough, elastic sealing performance, for joints requiring compression and extension greater than 35%.

PRODUCT INFORMATION: FEATURES & BENEFITS

- Solvent and isocyanate free, 100% solids
- Non-silicone
- Non-flammable
- Fast-curing
- Primerless bonding to most surfaces
- Paint compatible
- Low odor
- Extremely low shrinkage
- Non-staining
- Mildew resistant

STANDARDS & COMPLIANCE

- May contribute to LEED V4 EQ Material Resource Credit 4.1 - Adhesives and Sealants
- ASTM C920, Type S, Grade NS, Class 35 Uses NT, T, G, A & O
- Federal Specification TT-S-00230-C Type II, Class B
- Corps of Engineers CRD-C-541, Type II, Class B
- Conforms to OTC Rule for Sealants and Caulks
- Meets requirements of California Regs: CARB, BAAQMD and SCAQMD
- Conforms to USDA Requirements for Non-food Contact

COMMON APPLICATIONS

- Roofing
- Parapets
- Window and door frames
- Block and Masonry
- Expansion Joints
- Siding
- Weather Sealing
- Cove Joints
- Below-grade Waterproofing penetrations and transition details

HIGH PERFORMANCE DURABILITY

- Ultra-Guard® EFS can be installed on damp surfaces which is defined as when no moisture is transferred to the skin when the substrate is touched.
- The cured bead exhibits excellent long-term adhesion to the porous surfaces.
- Does not dry or become brittle.
- Low odor, ideal for indoor and outdoor use

Results may differ based upon statistical variations depending upon mixing methods and equipment, tempera

Property	Typical Value	Units	Test Method
VOC's	34.5 g/L		EPA Test Method 24
Skin over time 50% R.H. @70°F	30	Min.	ASTM C679
Density	12.7	lbs./gal.	ASTM D1875
Hardness	50	Shore A	ASTM D2240
Shear Strength	185.7	psi	ASTM D1002
Peel Strength		lbf/in.	ASTM D903
ABS Plastic	12.7		
Aluminum	25.1		
Mortar	25.7		
Glass	26.7		
Pine	24.0		
PVC	25.8		
Cold Rolled Steel	23.9		
Tensile	268	psi	ASTM D412
Elongation at Break	259	%	ASTM D412
Chemistry	Hybrid Polymer		
Movement	+/- 35%		ASTM C920
Shrinkage	0%		
Service Temperature	40°F - 200°F		
Viscosity	2,730,000	cps @ 1 rpm.	ASTM D2196-10
	1,555,000	cps @ 2 rpm.	
	460,000	cps @ 10 rpm.	

Ultra-Guard® EFS typical values represent data from multiple batches. Values will be refreshed, as necessary, upon data collection from additional campaigns and long-term variability discernment.

ULTRA-GUARD® EFS

Multi-purpose Sealant



APPLICATION

Remove all dirt, oil, loose paint, frost and other contamination from all working surfaces. Maintain Ultra-Guard® EFS at room temperature before applying to ensure easy gunning and tooling. Test and evaluate to ensure adequate adhesion. Carefully gun the sealant with a smooth, continuous bead. If tooling is needed, do so within fifteen minutes of application.

CONCRETE

Prior to application remove any residual contamination by mechanical abrasion, sand blasting or power washing. On green concrete, remove all release agents and loose concrete. Dry all visible and/or standing water. Install an appropriate backer rod to avoid three-point bonding.

METAL

Prepare all metal to ensure maximum adhesion. Remove all rust, scale and residue using a wire brush. Remove films, loose or inappropriate coatings and oils with an appropriate solvent such as alcohol.

*GMX recommends that coated substrates be tested for proper adhesion prior to starting a project to determine suitability for use.

WOOD

Wood should be clean, sound and dry prior to sealant application. Allow treated wood to weather for six months prior to application. Remove all coatings and paint to ensure proper adhesion. Ultra-Guard® EFS is not recommended for use on fire retardant lumber.

PRIMING

In most applications Ultra-Guard® EFS will not require a primer. However, certain substrates may require a primer to ensure a long-lasting bond and weatherproof seal. It is the applicator's responsibility to determine whether or not a primer is needed in their specific application.

CLEAN-UP

Clean tools and any uncured adhesive with mild solvent such as mineral spirits.

MATERIAL STORAGE/DISPOSAL

Store securely between 60° F - 80° F in unopened container. Recommended shelf life is 12 months from date of manufacture on bottom of tube. Keep tube tightly sealed. Dispose of contents/ container in accordance with Local/Regional/National/International Regulations. Refer to Safety Data Sheet (SDS) for further information.

SHELF LIFE AND STORAGE

The shelf life is 12 months for an unopened container from the date of manufacture. Reference the date of manufacture. YYMMDD ex. 190522 is May 22, 2019.

COLORS

Available only in BLACK



PACKAGING

There are 12, 20 oz. sausages in a case.

WARRANTY

GMX warrants that our products are manufactured and conform to strict quality assurance specifications. For warranty information visit: www.gmxwaterproofing.com/terms

LIMITATIONS

Ultra-Guard® EFS should not be used in applications in which it will be permanently exposed to liquid water.

PRECAUTIONARY STATEMENTS

Do not use until all instructions and safety precautions have been read and understood. Wear protective gloves, protective clothing and eye protection. Wash contaminated clothing before reuse. Contaminated work clothing should not be allowed out of the workplace.

IF ON SKIN: Wash exposed body areas with soap and water.

IF IN EYES: Rinse with water, remove contact lenses and continue rinsing. If exposed or concerned get medical advice/attention. Refer to Safety Data Sheet (SDS) for further information.



GMX, Inc.
3014 Chamber Dr.
Monroe, NC 28110
Toll Free: 866-228-7743
www.gmxco.com

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperatures, application methods, test methods, actual site conditions and curing conditions. Installation conditions and methods can impact product performance. Consult your local GMX Sales Representative for Questions.

PRIOR TO EACH USE OF ANY GMX PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS & INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT WWW.GMXCO.COM OR BY CALLING GMX AT 866-228-7743. NOTHING CONTAINED IN ANY GMX MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH GMX PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.